

AMENDMENTS TO THE CLAIMS

1. (Currently Amended) A method for producing a high loft, low density nonwoven web, the nonwoven web having X, Y and Z dimensions, with the X dimension being in a machine direction, the Y dimension being in a cross machine direction and the Z dimension being in a loft direction, comprising, in order:

a) forming a group of crimpable, substantially continuous, spunbond, bicomponent fibers of A/B configuration and depositing the group of fibers onto a forming surface without the addition of heat to the fibers before deposition;

b) first heating the fibers at a time and a temperature sufficient to induce a relaxation of molecular orientation of one side of the fiber while controlling or minimizing the forces which tend to impede crimping of the fibers whereby the fibers are allowed to crimp in the Z-direction with no more than a non-functional bonding of the fibers;

c) after the first heating, cooling the group of fibers below the temperature where the fibers will bond to each other and thereby inducing the fibers to crimp while controlling or minimizing the forces which tend to impede crimping of the fibers whereby the fibers are allowed to crimp in the Z-direction to produce the high loft, low density nonwoven web on a forming wire having a top side, a top side formation index, a wire side, and a wire side formation index such that the top side formation index differs from the wire side formation index by less than about 11%; and

d) bonding the crimped fibers of the high loft, low density nonwoven web in a manner to substantially maintain its high loft using a pattern of point bonds covering not more than 25% of an area of the nonwoven web.

2. (Canceled)

3. (Previously Presented) The method according to Claim 1 further comprising the step of placing the high loft, low density nonwoven web on a transportation sheet before pattern bonding.

4. (Canceled)
5. (Original) The method according to Claim 4 wherein the pattern bonding is a 5% to 10% surface area pattern bonding.
6. (Original) The method according to Claim 5 wherein the pattern bonding is a spiral bond.
7. (Original) The method according to Claim 1 wherein the high loft, low density nonwoven web has a basis weight of less than or equal to 1.5 osy (50 gsm).
8. (Original) The method according to Claim 1 further comprising: treating the high loft, low density nonwoven web with a surfactant selected to improve the hydrophilicity thereof.
9. (Original) The method according to Claim 1 further comprising: bonding at least one XY planar surface of the high loft, low density nonwoven web to a liquid barrier substrate.
10. (Original) The method according to Claim 9 wherein the liquid barrier substrate is breathable.
11. (Original) The method according to Claim 10 wherein the breathable liquid barrier substrate is a microporous film.
12. (Original) The method according to Claim 1 further comprising: bonding at least one XY planar surface of the high loft, low density nonwoven web to an expandable substrate.

13. (Original) The method of Claim 12 wherein the expandable substrate is elastic.

14. (Original) The method according to Claim 12 wherein the expandable substrate comprises filaments.

15. (Original) The method according to Claim 12 wherein the expandable substrate comprises a nonwoven web.

16. (Original) The method according to Claim 12 wherein the expandable substrate comprises a film.

17. (Original) The method according to Claim 13 wherein the expandable substrate comprises filaments.

18. (Original) The method according to Claim 13 wherein the expandable substrate comprises a web.

19. (Original) The method according to Claim 13 wherein the expandable substrate comprises a film.

20. (Previously Presented) The method of Claim 12 wherein the expandable substrate is retractable upon the application of heat.

21-63. (Canceled)

64. (Previously Presented) The method of Claim 1, wherein the fibers have a fiber denier of between about 0.1 dpf to about 9.0 dpf.

65. (Previously Presented) The method of Claim 1, wherein the fibers have a fiber denier of between about 0.1 dpf to about 5.0 dpf.

66. (Previously Presented) The method of Claim 1, wherein the fibers have a fiber denier of between about 0.1 dpf to about 3.3 dpf.

67. (Previously Presented) The method of Claim 1, wherein the fibers have a fiber denier of between about 3.4 dpf to about 4.2 dpf.

68. (Previously Presented) The method of Claim 1, wherein the fibers have a TiO_2 percentage of about 0.1% to about 5%.

69. (Previously Presented) The method of Claim 1, wherein the fibers of the nonwoven web are integrally bonded.

STATEMENT OF COMMON OWNERSHIP

The following statement is made in compliance with MPEP § 706.02(1)(2) and at the Examiner's request in the Office Action.

U.S. Patent Application 10/749,461 (instant application) and U.S. Publication 2003/0118816 ("Polanco") were, **at the time the invention of** U.S. Patent Application 10/749,461 was made, owned by Kimberly-Clark Worldwide, Inc.

Polanco was assigned to Kimberly-Clark Worldwide, Inc. via an Assignment recorded at Reel No. 012817, Frame No. 0703. The instant application was assigned to Kimberly-Clark Worldwide, Inc. via an Assignment recorded at Reel No. 0155533, Frame No. 0945.